



01/24/2024

114-Washed #4

Procedure	Sieve/Test	Average	Unit	Washed 4
	2" (50mm)	100.0	%	100-100
	1 1/2" (37.5mm)	96.8	%	90-100
	1" (25mm)	26.2	%	20-55
	3/4" (19mm)	8.4	%	0-15
	1/2" (12.5mm)	4.1	%	
	3/8" (9.5mm)	2.9	%	0-5
	1/8" (3.17mm)	1.2	%	
	#16 (1.18mm)	1.1	%	
	#200 (75µm)	0.77	%	0-2

Name/Title Jodi Kelly / Materials Performance Manager